

60 S. SEIBERLING ST.
P.O. BOX 9360
AKRON, OH 44305-0360
PHONE: (330) 798-9300
FAX: (330) 798-0214

TECHNICAL FAX: (330) 798-9328
SALES FAX: (330) 798-4089
WWW.HARWICKSTANDARD.COM

ISO 9001-2000 REGISTERED

## CPW-100 CHLORINATED PARAFFIN WAX

CPW-100 is a 100°C softening point, chlorinated paraffin wax containing 71.5% chlorine by weight. This products is useful in rubber and plastic compounds as a very efficient flame retardant as well as a plasticizer and extender. It is an excellent source of chlorine as a synergist with antimony oxide in flame retardant systems.

CPW-100 is available in either flaked or fine (50 mesh) powder form. The flaked form is very easy to handle and incorporates readily into rubber compounds using conventional mixing equipment. The powdered form may be the preferred physical form for many plastic compounds, especially polyester resins. The high chlorine content provides optimum flame resistance at relatively low concentrations. In addition, the resin form often provides improved physical properties and non-drip characteristics compared to the liquid halogenated products.

## TYPICAL PROPERTIES

Physical Form	Flakes or 50 Mesh Powder
Chlorine Content (Wt. %)	71.5
Specific Gravity	1.6
Stability: J.Q.D. Method	0.1
% HCl, 4 Hours @ 175°C	
Softening Point,°C	103

THE INFORMATION AND RECOMMENDATIONS CONTAINED HEREIN ARE BASED UPON DATA THAT ARE BELIEVED TO BE ACCURATE AND RELIABLE. APPLICATION AND PERFORMANCE INFORMATION ARE PROVIDED ONLY AS A GUIDE, SINCE THE CONDITIONS OF USE ARE BEYOND THE CONTROL OF HARWICK STANDARD DISTRIBUTION CORPORATION. CONSEQUENTLY, HARWICK STANDARD MAKES NO WARRANTIES, EXPRESS OR IMPLIED, WITH RESPECT TO THE GOODS OR USES OF THE GOODS OR THE PERFORMANCE OF THE GOODS AND MAKES NO WARRANTIES OF FITNESS FOR PARTICULAR PURPOSE OR MERCHANTABILITY. BUYER ACKNOWLEDGES THAT HARWICK STANDARD WILL NOT BE LIABLE FOR CONSEQUENTIAL, INCIDENTAL, DIRECT OR SPECIAL DAMAGES ARISING, DIRECTLY OR INDIRECTLY, IN RESPECT TO SUCH GOODS OR THE USE OR FAILURE THEREOF, WHETHER BASED ON BREACH OF WARRANTY, NEGLIGENCE, STRICT LIABILITY IN TORT OR OTHERWISE.