

PPG Silica Products offers a product line of synthetic amorphous precipitated silicas for use as reinforcing fillers in black, non-black, colored and translucent silicone compounds.

Compared to fumed silica, Hi-Sil™ silicas provide:

- Acceptable reinforcement at lower cost
- Significantly reduced crepe hardening
- Excellent compression-set resistance
- Excellent resistance to heat aging

Hi-Sil silicas can be used alone or in conjunction with fumed silica to extend the compound, increase hardness and reduce tackiness.

Hi-Sil **532EP** silica provides reinforcement (tear resistance) with increased hardness and dynamic properties (rebound) compared to crystalline silica (ground quartz).

Hi-Sil **900** reinforcing silica provides good tensile strength, tear resistance, compression-set, and good dynamic properties such as rebound.

Hi-Sil **135** silica combines relatively rapid incorporation and low Williams Plasticity with slightly higher tensile strength compared to *Hi-Sil* 900 silica.

Hi-Sil 132 silica has a higher surface area, builds viscosity more rapidly and leads to higher durometer than either *Hi-Sil* 900 or *Hi-Sil* 135 silica at equal loading.

Hi-Sil **915** silica yields high initial compound viscosity, but with less effect on durometer than *Hi-Sil* 132 silica. It also displays initial viscosity build without generating excessive crepe hardening normally associated with fumed silica.



Potential Applications

Sporting Goods

Wire and Cable Coatings

Conveyor Belts

Engine Mounts

Tire Treads



Product	N ₂ Surface Area, BET-5 (m ² /g)	N ₂ Surface Area, BET-1 (m ² /g)	рН	Na ₂ SO ₄ Wt. %	Particle Size (µm)
Hi-Sil 532EP	55	60	8	≤ 2	15
Hi-Sil 900	135	150	7	≤ 2	15
Hi-Sil 135	150	170	7	≤ 2	16
Hi-Sil 132	180	200	7	≤ 2	15
Hi-Sil 915	195	215	7	< 0.5	11

Samples

Samples are available upon request from Customer Service.

Storage

To ensure product integrity, PPG recommends that our silica products be stored under dry, clean conditions and protected against exposure to other substances. Since silica may pick up moisture, we also recommend that products that are stored for more than one year from the date of manufacture be re-tested for moisture content. There is no shelf life limit when stretch-wrapped palletized units or bags are kept under the above stated conditions. Pallets should not be doublestacked.

Safety and Health Effects

PPG Industries recommends that, before use, anyone using or handling this product thoroughly read and understand the information and precautions on the label, as well as in other product safety publications such as the Material Safety Data Sheet. Any health hazard and safety information contained herein should be passed on to your customers or employees, as the case may be. The products mentioned herein can be hazardous if not used properly. Like all potentially hazardous materials, this product must be kept out of the reach of children.

Packaging

Standard packaging as follows:

Net weight					
lb	kg	Bag Construction			
44	20	Multi-Wall Paper			
30	13.6	Multi-Wall Paper			
44	20	Multi-Wall Paper			
44	20	Multi-Wall Paper			
25	11.3	Multi-Wall Paper			
	1b 44 30 44 44	lb kg 44 20 30 13.6 44 20 44 20			

Please consult with Silica Customer Service or your Silica Sales Representative regarding additional packaging options, including custom package sizes and bulk shipments in Flexible Intermediate Bulk Container (FIBC), truckload, or railcar units.

Visit www.ppgsilica.com for MSDS and product specifications.



© 2011 PPG Industries, Inc. All Rights Reserved. Hi-Sil is a trademark and the PPG logo is a registered trademark of PPG Industries Ohio, Inc.

USA PPG Silica Products 440 College Park Drive Monroeville, PA 15146 USA

Customer Service: 1-800-243-6745 Technical Service: 1-800-764-7369 **EUROPE** PPG Industries Chemicals by Silica Products

P.O. Box 181 9930 AD Delfzijl, The Netherlands

Customer Service: +31-596-676710 Technical Service: +1-724-325-5171

Statements and methods presented are based upon the best available information and practices known to PPG Industries at present, but are not representations or warranties of performance, result or comprehensiveness. Further, the information provided herein, including any specific reference to patents of other persons or entities, is not to be taken as a license to operate under or a recommendation to practice any patents, copyrights, or any other intellectual property right of any person or entity.