

Specification

200 FCC

Solka-Floc®

Powdered Cellulose

DESCRIPTION

Basic Material	Powder Cellulose
Appearance	Fine Creamy White Powder

PHYSICAL AND CHEMICAL PROPERTIES

REFERENCE METHOD

Assay, % Cellulose	97.0 – 102.0	FCC
pH (10% suspension)	5.0 - 7.5	FCC
Loss on Drying, %	≤ 7.0	FCC
Water Soluble Substances, %	≤ 1.5	FCC
Ash (total), %	≤ 0.3	FCC
Chloride, %	≤ 0.05	FCC
Sulfur, %	≤ 0.01	FCC
Heavy Metals as Lead, ppm	≤ 2.0	FCC
Bulk Volume	2.1 ± 0.3 cc/g	Internal Test Method
Shelf Life, years	5 Dry, Room Temperature Conditions	

MICROBIOLOGY

Standard Plate Count	1,000 max	AOAC
Yeast and Mold	100 max	AOAC
<i>Salmonella</i>	Negative	AOAC
<i>E. coli</i>	Negative	AOAC
<i>S. aureus</i>	Negative	AOAC
<i>Listeria</i>	Negative	AOAC

PARTICLE SIZE DISTRIBUTION

Internal Test Method

Mesh:	<u>40-Mesh</u>	<u>100-Mesh</u>	<u>200-Mesh</u>
Retained:	<0.5%		
Thru:		≥NLT 90%	≥75%

REGULATORY COMPLIANCE

Ingredient Declaration:	
US - FDA	Powdered Cellulose
US - USDA	Powdered Cellulose
Canada – Health Canada	Powdered Cellulose
Kosher	
Halal	
GRAS	



Disclaimer: To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication. However, we do not assume any liability whatsoever for the accuracy and completeness of the above information.

Document ID: 18095	Title: TDS Solka-Floc 200 FCC	Version: 12	Issue Date: 1/14/2025 10:59:10 AM
------------------------------	-----------------------------------------	-----------------------	---------------------------------------------