WELLPREN TM

CHLORINATED POLYETHYLENE RESIN

WELLPREN TM

IM 898M

Version: 02 Revision date: 01 Jan.2017

General introduction

WELLPREN TM RESIN IM series products are chlorinated polyethylene resin. It is a type of superior high performance-price ratio impact modifier and is widely used in production of many types of rigid plastic products and semi-flexible products.

Proper amount of WELLPREN TM RESIN added into formulations of PVC, PE or PP plastic products will not only greatly enhance impact resistance but will also largely improve low temperature performance, weatherability, welding strength and other performance. WELLPREN TM RESIN is most suitable for substitution of acrylic impact modifier (AIM) or blending with AIM with a certain percentage without adjusting the processing data and the formulation, resulting in an optimum performance/cost solution.

Properties of WELLPREN TM RESIN:

- Superior flexibility and good low temperature impact strength
- Compatible with acrylic impact modifier
- Superior compatibility with polymers like PVC, PE, and ABS
- Superior weatherability
- Superior processibility
- Excellent corner strength
- High surface gloss
- Good filler acceptance
- Cost effective system

Characteristics of IM 898M

Among all WELLPREN TM IM series, IM 898M is a improved version of IM888 which has the best impact strength and is free flowing.

Application

For high impact application, can be loaded in super sack.

Property	Test method	Typical data	Specification
IM898M			
Appearance		White powder	White powder
Chlorine content, %	GB/T7139	35	34 - 36
Heat of fusion, J/g	HG/T2704-2010	0.8	≤ 1.5
Volatiles, %	GB/T2914	0.2	\leqslant 0.3
Sieve remainder, 0.8 mm sieve, %	GB/T2916	0	≤ 2.0
Bulk density, g/cm ³	GB/T-20022-2005	0.51	≥ 0.48
Impurity particles, piece/100g	SD/T - 2705	8	≤ 15
Thermal stability time, min @ 165° C	GB/T-2917.1-2002	10	≥ 8
Hardness, Shore A	GB/T531	56	≤ 60
Tensile strength, Mpa	GB528	12.0	≥ 10.0
Elongation at break, %	GB528	750	\geq 700

Supply specification

Packing, transportation and storage

25 Kg PP woven bag or 500 kg / 600 kg supre sacks.

This material is non- dangerous goods for land, air and marine transportation.

To avoid blocking, bags containing WELLPREN should be stacked no more than two pallets high and should be stored at temperature no more than 100° F (38° C), shelf life is theoretically unlimited when storage is under proper conditions.

Safe Handling

Please consult the MSDS before handling for additional information concerning

personal protective equipment, Safety, Health and Environmental information, and always exercise the utmost care in handling.

Contact information



Sundow Polymers Co.LTD

http://www.sundow.com

info@sundow.com

Fl.8, Riverdals Bld.,No.350, Dongfeng Street, Weifang,Shandong, China. Tel: + (86) 536 8057068 Fax: +(86) 536 8057018