

60 S. SEIBERLING ST. P.O. BOX 9360

AKRON, OH 44305-0360 PHONE: (330) 798-9300

FAX: (330) 798-0214

TECHNICAL FAX: (330) 798-9328

SALES FAX: (330) 798-4089

ISO 9001-2000 REGISTERED

CHAMPION CLAY
HARD CLAY

Southeastern Champion is a high quality, air floated sedimentary hard kaolin clay. Strict attention to production and quality control measures assure a high degree of uniformity.

## TYPICAL PHYSICAL PROPERTIES

Screen Residue 0.25% Maximum on a 325 Mesh Screen

Free Moisture Less than 1%

Specific Gravity 2.60

Color Light Cream Acidity of Clay (pH)  $4.75 \pm .75$ 

Particle Size 92% finer than 2 microns

Ignition Loss 14% + 1.0%

Surface - Mean Diameter

By Air – Permation Test 0.6 Microns

Oil Absorption 36ml Oil/100gm Clay ± 6ml

## **QUANTITIVE ANALYSIS**

Silica (SiO <sub>2</sub> )	43.2 - 44.5%
Aluminum Oxide (Al <sub>2</sub> O <sub>3</sub> )	38.5 - 39.5%
Iron Oxide (as Fe <sub>2</sub> O <sub>3</sub> )	1.44 - 1.78%
Titanium Dioxide (TiO <sub>2</sub> )	1.00 - 2.00%
Maganese Oxide (MnO <sub>2</sub> )	None
Magnesium Oxide (MgO)	Faint Trace
Calcium Oxide (CaO)	Faint Trace
Potassium Oxide (K <sub>2</sub> O)	Faint Trace
Sodium Oxide (Na <sub>2</sub> O)	Faint Trace

## RECOMMENDED APPLICATIONS

Kaolin clays are chemically inert and are very effective fillers/extenders in a variety of industrial applications such as rubber compounds, plastics, paints, adhesives, roofing granules, ceramics, paper fillers and coatings just to name a few. Champion Clay is ideal for use in rubber compounds and plastics where fineness and color consistency are important.

Champion Clay is manufactured by Southeastern Clay Company

THE INFORMATION AND RECOMMENDATIONS CONTAINED HEREIN ARE BASED UPON DATA THAT ARE BELIEVED TO BE ACCURATE AND RELIABLE. APPLICATION AND PERFORMANCE INFORMATION ARE PROVIDED ONLY AS A GUIDE, SINCE THE CONDITIONS OF USE ARE BEYOND THE CONTROL OF HARWICK STANDARD DISTRIBUTION CORPORATION. CONSEQUENTLY, HARWICK STANDARD MAKES NO WARRANTIES, EXPRESS OR IMPLIED, WITH RESPECT TO THE GOODS OR USES OF THE GOODS OR THE PERFORMANCE OF THE GOODS AND MAKES NO WARRANTIES OF FITNESS FOR PARTICULAR PURPOSE OR MERCHANTABILITY. BUYER ACKNOWLEDGES THAT HARWICK STANDARD WILL NOT BE LIABLE FOR CONSEQUENTIAL, INCIDENTAL, DIRECT OR SPECIAL DAMAGES ARISING, DIRECTLY OR INDIRECTLY, IN RESPECT TO SUCH GOODS OR THE USE OR FAILURE THEREOF, WHETHER BASED ON BREACH OF WARRANTY, NEGLIGENCE, STRICT LIABILITY IN TORT OR OTHERWISE.