



Product Data Sheet *Epolene*® C-15P Polymer

Application/Uses

- Automotive refinish
- Automotive
- Building and Construction
- Hot Melt Adhesives
- Packaging
- Solvent borne Adhesives
- Wax Modification

Key Attributes

- Enhances paraffin wax coating properties like gloss, grease resistance, and MVTR
- Excellent thermal stability
- Low color
- Medium molecular weight
- Useful in color concentrates

Product Description

Epolene C-15P is a branched low density polyethylene homopolymer powder with low color and medium molecular weight. It is useful as a base polymer for adhesives and coatings, color concentrate dispersions, and to provide lubricity in rubber compounding. Coatings produced with *Epolene* C-15P exhibit high gloss, low moisture vapor transmission rates, grease resistance, and good heat seal ability.

Typical Properties

| Property | Test Method | Typical Value, Units |
|-----------------------------------|-------------|----------------------|
| Polymer Type | | PE |
| Mettler Softening Point | ASTM D6090 | 98°C |
| Penetration Hardness ^a | ASTM D 5 | 4 dmm |
| Viscosity, Brookfield | | |
| @ 125°C (257°F) | | 8,950 cP |
| @ 190°C (374°F) | | 1,800 cP |
| Molecular Weight ^b | | 17,000 |
| Form | | Powder |

^a Needle under 100-g load for 5s @ 25 deg C, tenths of mm

^b Molecular weight measured via Gel Permeation Chromatography (GPC) using polystyrene standards

Comments

Properties reported here are typical of average lots. Westlake makes no representation that the material in any particular shipment will conform exactly to the values given.

Compatibility and Solubility

Epolene polymers are compatible with many polymers, resins, and natural and synthetic waxes.

Packaging

Epolene C-15P polymer is supplied as free-flowing powder, packaged in multiwall paper bags with a polyethylene coated inner liner [40 lb net weight]. The bags are palletized and stretch wrapped to prevent contamination during storage and shipment. Many *Epolene* polymers are also shipped in a variety of bulk containers.

Epolene C-15P polymer is also available in pellet form as *Epolene* C-15 polymer.

Storage

The useful life of this product can be affected by storage and handling conditions. When stored in the original unopened container in an enclosed area and protected from moisture, extreme temperatures and contamination, this product is estimated to continue to meet applicable sales specifications for more than 4 years from the date of manufacture. First in first out (FIFO) inventory control is recommended.

It is your responsibility to determine that our product is safe, lawful and technically suitable for your intended uses. Please note that this letter is provided to you as one of the means to assist you in analyzing our product, and does not serve to modify or amend our sales contract or sales arrangement.

Westlake Polymers LLC does not endorse or claim suitability of its products for any particular application. **WESTLAKE MAKES NO WARRANTY OF MERCHANTABILITY AS TO ITS PRODUCTS. WESTLAKE POLYMERS LLC MAKES NO WARRANTIES, EXPRESS OR IMPLIED, CONCERNING THE SUITABILITY or FITNESS OF ANY WESTLAKE PRODUCT FOR ANY PARTICULAR PURPOSE.** Westlake's liability and customer's exclusive remedy for any claims arising out of sales of its products are expressly limited at customer option to replacement of non-performing goods or payment not to exceed the purchase price plus transportation charges thereon in respect to any material which damage is claimed.