

# TBP masterbatch (Sulfur donor)

#### OH POLY-TERT-BUTYLPHENOLDISULFIDE Molecular Weight : Polymer CAS 60303-68-6 **EINECS** . tert-Bu . tert-Bu Active Colour Filtration Mooney ML (1+4) Density PRODUCT 80°C Content N for Natural (%) P for Pigment **Typical value** Typical value (µm) **TBP 75 GA F100** 75 Beige\* (N) 100 10 1.15

GA: Granules co-polymer of acetate/acrylate & polyethylene

#### ACTIVE MATERIAL TYPICAL VALUES

Softening point : 105° C

#### REMARKS

Non-staining, non-discolouring Non-blooming Odourless

\* Depending on natural variation of raw material

#### **PROPERTIES**

Mixland+<sup>®</sup> TBP masterbatch is a general purpose sulfur donor accelerator with a medium speed cure. It is an efficient curing agent. It is suitable for NR, IR, SBR, BR, NBR and EPDM.

It can replace TMTD to switch to a nitrosamine-free curing system or OTOS, which is CMR product.

For more information, please refer to MLPC Technical Report available for NR, NBR or EPDM compound. Mixland+<sup>®</sup> TBP masterbatch exhibits several properties:

- Is a sulfur donor (~15%), so it is able to prevent reversion
- Has no nitrogen in its formula: so fully nitrosamine free
- The phenolic function acts as a weak antioxidant
- Due to the fact it is an oligomer, TBP has tackifiant properties
- Improves co-vulcanization

#### **APPLICATIONS**

EPDM profiles, industrial goods, tires parts, AVS...

#### **PACKAGING & STORAGE**

Cardboard box weight : 25 kg net Standard CP3 pallet : 600 kg - Do not pile more than 2 pallets height Shelf-life : **2 years** in its original packaging Store in a dry and cool place and away from direct sources of heat or sunlight.

#### **SAFETY & TOXICITY**

For detailed information, please refer to our Material Safety Data Sheet.

## NITROSAMINE FREE

#### MIXLAND+® MASTERBATCH ALLOWS:

- Dust free products with a high level of filtration up to 100µ
- Tack free products at room temperature
- Lower Mooney viscosity, improving quality of dispersion
- Scrap rate reduction thanks to filtration
- Wider compatibility with elastomers

The information contained in this leaflet is based on tests carried out by our laboratories and data selected from the literature but shall in no event be held to constitute or imply any warranty or undertaking. No liability whatsoever can be accepted with regard to the handling, processing or use of the products concerned, which must in all cases be employed with regard to all relevant regulations and/or legislation in the country or countries concerned.

### Issued 8 dated March 2020

#### MLPC International

209, Avenue Charles Despiau – 40370 Rion des Landes - France Tel.: +33 (0)5 58 57 02 78 – Contact : commercial@mlpc-intl.com http://www.mlpc-intl.com

# **TECHNICAL DATA SHEET**



#### Marketed By Harwick Standard Distribution Corporation

(330) 798-9300